

<h1 style="color: red; margin: 0;">Nero Marquina</h1> <p>Aulestia Marquina, Viscaya, Spain</p>		<p style="font-size: 0.8em; margin-top: 5px;">MEKANISKE STENHUGGERI A/S GRUNDLAGT 1797</p>
--	--	--

DS: EN 12058	Internal Flooring of Natural Stone	Date of Test: 2008
DS: EN 1341	External Paving of Natural Stone	Date of Test: N/A
DS: EN 1469	External Cladding of Natural Stone	Date of Test: N/A

General for all use:

Dimensions and dimensional variation	Complies
Nominal thickness an variation	Complies
Release of dangerous substances	None in conditions of use as Internal-/External Flooring, External Paving or Cladding
Fire performance	Deemed to satisfy
Reaction to fire	Deemed to satisfy

Internal Flooring and Stairs:

Waterabsorption acc. to DS: EN 13755	0,19%		
Bending/Flexural strength acc. to DS: EN 12372	13,44 N/mm ²		
Density acc. to DS: EN 1936	2,71 kg/cm ³		
Compression Strength acc. to DS: EN 1926	N/A		
Petrografic evaluation acc. to DS: EN 12407	Limestone		
Mineralogical composition (by weight)	Cao > 50%		
Slip resistance in dry	N/A	Slip resistance in wet	N/A

External Flooring, Cladding and Stairs:

Porosity DS: EN 1936	N/A		
Density DS: EN 1936	2,71 kg/cm ³		
Water absorption DS: EN 13755	0,19%		
Bending strength DS: EN 12372	N/A		
Durability / Freeze thaw cycling	complies		
Compressive strength DS: EN 1926	N/A		
Breaking load at dowl hole DS: EN 13364	N/A		
Durabiliyy / Thermal cycling	N/A		
Determination of resistance to salt crystalization DS: EN 12370	N/A		