

Forest Grey



MEKANISKE STENHUGGERI A/S
GRUNDLAGT 1797

DS: EN 12058	Internal Flooring of Natural Stone	Date of Test: 2005
DS: EN 1341	External Paving of Natural Stone	Date of Test: N/A
DS: EN 1469	External Cladding of Natural Stone	Date of Test: 2005

General for all use:

Dimensions and dimensional variation	Complies
Nominal thickness an variation	Complies
Release of dangerous substances	None in conditions of use as Internal-/External Flooring, External Paving or Cladding
Fire performance	Deemed to satisfy
Reaction to fire	Deemed to satisfy

Internal Flooring and Stairs:

Water absorption acc. to DS: EN 13755	0,10%		
Bending/Flexural strength acc. to DS: EN 12372	9,5 Mpa		
Density acc. to DS: EN 1936	2843 kg/m ³		
Compression Strength acc. to DS: EN 1926	N/A		
Petrografic evaluation acc. to DS: EN 12407	Gabbro		
Mineralogical composition (by weight)	N/A		
Abrasion resistance EN 14157	17,4 mm		
Slip resistance in dry	Polished 52	Slip resistance in wet	Polished 13

External Flooring, Cladding and Stairs:

Porosity DS: EN 1936	N/A
Density DS: EN 1936	2843 kg/m ³
Water absorption DS: EN 13755	0,10%
Bending strength DS: EN 12372	9,5 Mpa
Determination of frost resistance DS: EN 12371	N/A
Compressive strength DS: EN 1926	N/A
Breaking load at dowl hole DS: EN 13364	754 N
Determination of ageing by Thermal shock	-0,01%
Determination of resistance to salt crystalization DS: EN 12370	N/A